

Standard Specification for Zinc Dust Pigment¹

This standard is issued under the fixed designation D 520; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers three types of zinc dust, for use as a pigment in paints.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

2. Referenced Documents

2.1 ASTM Standards:

B 214 Test Method for Sieve Analysis of Granular Metal Powders²

D 185 Test Methods for Coarse Particles in Pigments, Pastes, and Paints³

D 521 Test Methods for Chemical Analysis of Zinc Dust (Metallic Zinc Powder)³

E 40 Test Methods for Chemical Analysis of Slab Zinc (Spelter)⁴

3. Composition and Properties

3.1 The pigments shall consist substantially of metallic zinc and shall conform to the requirements for composition prescribed in Table 1.

3.2 In such physical properties as are specified by the purchaser, the pigment shall satisfactorily match a reference sample mutually agreed upon between the purchaser and the seller.

4. Sampling

4.1 Two samples shall be taken at random from different packages from each lot, batch, day's pack, or other unit of production in a shipment. When no markings distinguishing between units of production appear, samples shall be taken from different packages in the ratio of two samples for each

¹ This specification is under the jurisdiction of ASTM Committee D-1 on Paint and Related Coatings, Materials, and Applications, and is the direct responsibility of Subcommittee D01.31 on Pigment Specifications.

Current edition approved April 10, 2000. Published June 2000. Originally published as D520 – 39 T. Last previous edition D520 – 84 (1995) ^{ϵ 1}.

² *Annual Book of ASTM Standards*, Vol 02.05.

³ *Annual Book of ASTM Standards*, Vol 06.03.

⁴ *Annual Book of ASTM Standards*, Vol 03.05.

TABLE 1 Requirements for Composition

	Type I	Type II	Type III
Total zinc, calculated as Zn, min, %	97.5	98.0	99.0
Metallic zinc, min, %	94.0	94.0	96.0
Material other than metallic zinc, ZnO, and admixed CaO, where applicable max %	0.75
Calcium, calculated as CaO, max, %	0.7	0.7	...
Lead, calculated as Pb, max, %	...	0.01	0.002
Iron, calculated as Fe, max, %	...	0.02	0.002
Cadmium, calculated as Cd, max, %	...	0.01	0.001
Chlorine, calculated as Cl, max, %	...	0.01	...
Sulfur, calculated as SO ₂ , max, %	...	0.01	...
Moisture and other volatile matter, max, %	0.10	0.10	0.10
Oily or fatty matter, or both, max, %	...	0.05	...
Zinc oxide (ZnO), max, %	6.0	remainder	remainder
Coarse particles, max, %:			
Total residue retained on a 150- μ m (No. 100) sieve	none	0.1	0.1
Total residue retained on a 75- μ m (No. 200) sieve	...	0.8	0.8
Total residue retained on a 45- μ m (No. 325) sieve	4.0	3.0	3.0

5000 kg (10 000 lb), except that for shipments of less than 5000 kg, two samples shall be taken. At the option of the purchaser, the samples may be tested separately or after blending in equal quantities the samples from the same production unit to form a composite sample.

5. Test Methods

5.1 Tests shall be conducted in accordance with the following ASTM test methods. Test procedures not covered by these ASTM test methods shall be mutually agreed upon between the purchaser and the seller.

5.1.1 *Total and Metallic Zinc*—Test Methods D 521.

5.1.2 *Lead, Cadmium, and Iron*—Sections 8, 18.2, and 22, respectively, of Test Methods E 40.

5.1.3 *Oily or Fatty Matter, or Both*—Test Methods D 521.

5.1.4 *Coarse Particles*—Test Method B 214 or Test Methods D 185.

6. Keywords

6.1 pigment; zinc

 **D 520**

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).